

Swisspearl Patina Original



Datasheet - Facade Boards

Swisspearl Patina Original has a natural, textured surface. You can see the fibre and natural characteristics of the raw materials, and you can see and feel the unique sanding lines on the surface. Natural imperfections like dots and spots can be visible but from 3-5 meters distance the surface will appear homogenous. As the seasons change and the years pass, the natural ageing of the fibre cement leaves subtle traces on the surface, and the facade will gradually acquire a distinctive patina.


Swisspearl Patina Original is a through coloured board. Variations in the colour of the board are visible and vary depending on the orientation of the sheet, the viewing angle and level of light and humidity. Measuring the board colour small variations in the colour lightness are accepted. Swisspearl facade boards are high quality fibre cement products used as part of a ventilated facade solution in all types of constructions.

Dimensions (nominal)		Small Module	Standard size
Thickness	mm		6
		8	8
			12
Width	mm	292	1192
		592	1250
Length	mm	1192	2500
		2392	3050
		2992	


Standard size



Project size



Small Modules



www.swisspearl.com

Please visit the local website for contact details and further information.

Swisspearl Patina Original

Dimension tolerance (EN 12467, Level 1)		Patina 6 mm	Patina 8 mm	Patina 12 mm
Thickness (up to 20 mm)	mm	± 0.6	± 0.8	± 1.2
Width (a ≤ 1000 mm)	mm	± 3.0	± 3.0	± 3.0
Width/Length (1000 mm < a ≤ 1600 mm)	mm	± 0,3% a	± 0,3% a	± 0,3% a
Length (1600 mm < Length)	mm	± 5.0	± 5.0	± 5.0

* a is the nominal width or length

Physical properties

Density, dry minimum (EN12467)	kg/m ³	≥ 1250	≥ 1250	≥ 1250
Density, dry average (EN12467)	kg/m ³	1417	1431	1487
Weight (incl. 10% moisture)*	kg/m ²	9.4	12.6	19.6
Moisture content (on dispatch ex works)	%	5-10	5-10	5-10

* nominal value may vary depending on the conditions

Mechanical properties (EN 12467)

Flexural modulus				
E-module along grain, ambient	GPa	12	12	NA
E-module across grain, ambient	GPa	13	14	NA
E-module along grain, wet	GPa	9	9	NA
E-module across grain, wet	GPa	11	11	NA

Bending strength (EN 12467)

Along grain, wet	MPa	18	18	18
Across grain, wet	MPa	29	28	26

Modified Charpy Pendulum Impact test EN ISO 148-1

Along grain, dry	kJ/m ²	2.2	2.7	NA
Across grain, dry	kJ/m ²	2.7	3.6	NA

Thermal properties

Thermal conductivity (ISO 8301, EN 12667), λ ₁₀	W/mK	0.32	0.37	NA
Coefficient of thermal expansion	mm/m °C	0.01	0.01	NA
Frost resistance (average along/across)	R _L	≥0.75	≥ 0.75	≥ 0.75

www.swisspearl.com

Please visit the local website for contact details and further information.

Swisspearl Patina Original

Hygrothermal properties

Water absorption (24 hrs 105°C, 24 hrs in water)	%	28	28	28
Moisture movement (30/90 % RH, EN 12467)	%	0.08	0.08	0.08

Water vapour transmission properties (EN 12572-C)

Water vapour transmission resistance (Z-value)	GPa m ² s/kg	2.4	2.5	NA
Water Vapour transmission resistance (Z-value)	s/m	17700	18500	NA
Water vapour diffusion equivalent air layer thickness, Sd	m	0.5	0.5	NA
Water vapour resistivity	MN s/gm	366	327	NA
Water vapour resistance factor, μ		58	58	NA
Water vapour resistance	MN s/g	2.4	2.5	NA
Water vapour transmission	USPerm	7.2	7.0	NA

Color variation measured on the production line

CIELAB colour model	ΔL	-2.5/+2.5	-2.5/+2.5	-2.5/+2.5
---------------------	------------	-----------	-----------	-----------

Fire Performance

Reaction to fire (EN 13501-1)	Rating	NA	A2-s1, d0	A2-s1, d0
Behavior of materials at 750°C (ASTM E136)	Rating	NA	Passed	NA
External thermal insulation for walls (BS 8414-2-2015+A1-2017)*	Rating	NA	Passed	NA

* Tested with special requirements. Contact Product Compliance for further informations.

Other properties

Category, class (EN12467)	NT A4 I	NT A4 I	NT A4 I
M1-Classification, VOC emission of building materials	Pass	Pass	Pass

Impact resistance test (ETAG 034, ISO 7892), 8 mm

	Max.	Category IV	Category III	Category II	Category I
Hard body	1 Joule	Passed			
	3 Joules		Passed	Passed	Passed
	10 Joules			Passed	Passed
Soft body	10 Joules	Passed	Passed		
	60 Joules			Passed	Passed
	300 Joules			Not passed	
	400 Joules				Not passed
Evaluation		Passed	Passed	Not passed	Not passed

www.swisspearl.com

Please visit the local website for contact details and further information.

Swisspearl Patina Original

Ballwurfsicherheit (DIN 18032-3) - (Impact resistance), Wall and Ceiling, 12 mm

	Angle of Impact	Number of shots	Subconstruction	Distance, subconstruction	Test result
Handball	90	30	Aluminium	315 mm	Passed as "Ballwurfsicher"
	45	12			
	45	12			
Hockeyball	90	4	Aluminium	315 mm	Passed as "Ballwurfsicher"
	45	4			
	45	4			
