

Swisspearl Patina Inline

Datasheet - Facade Boards


Swisspearl Patina Inline introduces a 3D-effect to your building from the milled linear grooves in the board. The featured lines in combination with the natural light and viewing angle gives a lively facade changing its appearance throughout the day. As the seasons change and the years pass,

the natural ageing of the fibre cement leaves subtle traces on the surface, and the facade will gradually acquire a distinctive patina. As if formed by nature Swisspearl Patina Inline adds a natural stylish finish to your facade. Swisspearl Patina Inline will patinate with time - enriching its natural appearance.

Dimension (nominal)

Thickness	mm	9,5 / 8
Width	mm	1192 1250
Length	mm	2500 3050

Standard size



www.swisspearl.com

Please visit the local website for contact details and further information.

Swisspearl Patina Inline

Dimension tolerance (EN 12467, Level 1)

Thickness	mm	+/- 10%
Width (1000mm < a < 1600mm)	mm	± 0,3% a
Length (1600mm < Length)	mm	± 5.0

Physical properties

Density, dry minimum (EN 12467)	kg/m ³	≥ 1300
Density, dry average (EN 12467)	kg/m ³	1430
Weight (incl. 10% moisture)*	kg/m ²	14.2

* Nominal value may vary depending on the conditions

Mechanical properties (EN 12467)

Flexural modulus		
E-module along grain, ambient	GPa	17
E-module across grain, ambient	GPa	17
E-module along grain, wet	GPa	13
E-module across grain, wet	GPa	14

Bending strength (EN 12467)

Along grain, ambient	MPa	26
Across grain, ambient	MPa	37
Along grain, wet	MPa	21
Across grain, wet	MPa	32

Impact strength (Pendulum test)

Along grain, dry	kJ/m ²	2.9
Across grain, dry	kJ/m ²	2.8

Thermal properties

Thermal conductivity (ISO 8301, EN 12667), λ ₁₀	W/mK	0,4
Coefficient of thermal expansion	mm/m °C	0.01
Frost resistance (average along/across)	R _L	≥0.75

Hygrothermal properties

Moisture movement (30/90 % RH, EN 12467)	%	0,07
Water impermeability (EN 12467)	Visual	No drop

www.swisspearl.com

Please visit the local website for contact details and further information.

Swisspearl Patina Inline

Color variation measured on the production line

CIELAB colour model	ΔL	-2.5/+2.5
---------------------	------------	-----------

Fire Performance

Reaction to fire (EN 13501-1)	Rating	A2-s1, d0
-------------------------------	--------	-----------

Other properties

Category, class (EN 12467)	NT A4 1
----------------------------	---------

M1-Classification, VOC emission of building materials	Pass
---	------

www.swisspearl.com

Please visit the local website for contact details and further information.
